



# LIFE PAINT

## PRODUCT SPECIFICATIONS

### 88-60 EPOXY ROOF PRIMER

**88-60 is a two-component, water based, epoxy primer designed for the 88-50 silicone top coat. 88-60 has unique penetrating characteristics and rust inhibitive properties.**

#### Features & Benefits

- Rust Inhibitor
- Low Odor
- Fast Recoat Time
- Low Viscosity

#### Packaging:

5 Gal Kit (4:1)

#### Directions:

**MIXING:** Review all technical data sheets, system sheets, labels, instructions, MSDS, and Guide Specifications before mixing and applying. Mix 4 Parts A with 1 Part B thoroughly to ensure a homogeneous material. The combined components should be thoroughly mixed using a mechanical mixer at slow speed. Mix only the amount that you can use after mixing within 30 minutes.

**Clean Up:** Equipment should be cleaned with water immediately after use. Dried material will require an environmentally safe solvent to remove.

**APPLICATION:** Prior to coating any surface, be sure the coating will adhere by performing an adhesion test (ASTM D-903). Apply at a rate of 200-300 square feet per gallon. Coverage rate will depend on surface roughness and porosity. Do not allow the material to puddle. Coating may be applied by brush, phenolic resin core roller, or airless spray equipment. Do not apply when temperatures are below 50°F (4.4°C) or when precipitation is in forecast within 48 hours. Higher temperatures and/or high humidity will significantly accelerate the cure time and pot life. Use caution in batch sizes and thickness of application. Allow product to dry tack free before applying the top coat.

#### Storage & Handling:

Keep containers closed and store in a dry, cool place away from heat, sparks, open flame, excessive heat, and moisture. Keep material stored above 65°F (18°C). Open containers should be blanketed with dry nitrogen before resealing. Shelf life: 6 months.

#### Safety:

Review the Material Safety Data Sheets (SDS or MSDS) and container labels for detailed health and safety information.

#### SKIN CONTACT

To prevent excessive skin contact with the sprayed product, we recommend use of fabric coveralls and neoprene or other resistant gloves.

#### EYE CONTACT

Wear protective goggles when working with product. See SDS or MSDS in case of eye contact.

Please read all information in the general guidelines, technical data sheets, application guide, and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local LIFE PAINT representative for current technical data and instructions.

**DISCLAIMER:** All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazards listed herein are the only ones that may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether verbal or in writing, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and LIFE PAINT makes no claim that these tests or any other tests, accurately represent all environments.

#### PHYSICAL PROPERTIES

Shelf Life	1 Year (unopened container)
Mixing Ratio	4A:1B (volume)
Pot Life	30 Minutes
Weight Per Gallon	9.31 pounds (mixed)
Solids	(w) 45%±2% (mixed) (v) 39%±2% (mixed)
VOC	43 g/l (0.36 lbs/gal) (mixed)

# 88-55 TPO PRIMER ROOF COATING

## Technical & Physical Properties

See Application Specifications for additional information.

An older roof in poor condition may need a new roof.

Physical Property	Result
Solids	97% (w) 97% (v)
Viscosity	500 +/- 100 cps
VOC	25 g/l
Pot Life	60 minutes

The maximum V.O.C. of this product does not exceed 50 grams/liter. WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).